

## Bitumen Specification

### Penetration Grade Analysis 85/100

Specification	Acceptable Range	Result	Test Method	Explanations
Penetration	85-100	91	ASTM – D5	at 25°c , mm/10
Softening Point	45-53	45.4	ASTM – D36	°c
Ductility	+100	>100	ASTM – D113	at 25°c , cm
Solubility	99.0 Min	99.87	ASTM – D2042	in CCL4 , %
Specific Gravity	1.01-1.06	1.01	ASTM – D70	at 25°c
Spot Test	Negative	Negative	T102	in Naphtha
Flash Point	220 Min	334	ASTM – D92	°c
Kinematic Viscosity	....	287	ASTM – D4402	at 135°c , c.st
Absolute Viscosity	....	1164	ASTM – D4402	at 60°c , Poises
<b>Test on Residue From Thin Film Oven Test (T.F.O.T)</b>				
Drop in Penetration	20 Max	8.9	ASTM – D5&D6	%
Mass Loss	0.2 Max	0.11	ASTM – D6	Wt%

**UAE OFFICE:**

Unite 801, Al Salemiyah tower, Rigga Al Buteen road, Dubai, United Arab Emirate, PO Box No: 384588

**Website:** [essfuture.com](http://essfuture.com) | **E-mail:** [info@essfuture.com](mailto:info@essfuture.com)