

Slag cement

Physical Specifications:

BS992

Physical elements	Blain (cm ² /gr)	Initial setting time (min)	Final setting time (min)	Compressive strength (kg/cm ²)				Autoclave expansion (%)
				2 days	3 days	7 days	28 days	
Cement	3600	190	240	170	220	350	490	0.08
Standard deviation	150	30	35	15	20	25	25	0.04
National Iranian Standard	>2800	>45	<420	-	>100	>180	>300	<0.50
EN 197-1	-	>75	-	-	-	>160	>325	-

Chemical Specifications:

Chemical elements	SiO ₂ %	Al ₂ O ₃ %	Fe ₂ O ₃ %	CaO %	MgO %	Cl %	SO ₃ %	L.O.I %	I.R %	Free CaO %	Total Alcalis %	S-- %	Cr+6 %
Cement	23.70	5.90	3.40	58.10	3.60	0.025	2.20	1.75	0.40	1.30	0.75	0.35	<0.009
Standard deviation	0.80	0.50	0.30	1.20	0.40	0.005	0.35	0.40	0.20	0.30	0.05	0.15	-
National Iranian Standard	-	-	-	-	-	-	<3.00	<3.00	<1.00	-	-	<2.00	-
EN 197-1	-	-	-	-	-	<0.100	<3.50	<5.00	<5.00	-	-	-	-

UAE OFFICE:

Unite 801, Al Salemiyah tower, Rigga Al Buteen road, Dubai, United Arab Emirate, PO Box No: 384588

Website: essfuture.com

E-mail: info@essfuture.com

UAE TEL: +97508861747