

portland Cement type 5

Physical Specifications:

Physical elements	Blain (cm ² /gr)	Initial setting time (min)	Final setting time (min)	Compressive strength (kg/cm ²)				Autoclave expansion (%)
				2 days	3 days	7 days	28 days	
Cement	3300	190	240	170	220	330	510	0.08
Standard deviation	150	30	35	15	20	25	25	0.03
National Iranian Standard	>2800	>45	<360	-	>85	>150	>270	<0.80
EN 197-1	-	>60	-	>100	-	-	>425	-

Chemical Specifications:

Chemical elements	SiO ₂ %	Al ₂ O ₃ %	Fe ₂ O ₃ %	CaO %	MgO %	Cl %	SO ₃ %	L.O.I %	IR %	Free CaO %	Total Alkalis %	C ₃ A %	2C ₃ A+ C ₄ AF %	Cr+6 %
Cement	20.85	4.50	5.10	63.50	2.15	0.025	1.90	1.10	0.35	1.30	0.65	3.50	21.00	<0.009
Standard deviation	0.40	0.25	0.25	0.50	0.20	0.005	0.30	0.40	0.20	0.30	0.05	1.00	1.50	-
National Iranian Standard	-	-	-	-	<5.00	-	<2.30	<3.00	<0.75	-	<0.80	<5.00	<25.00	-
EN 197-1	-	-	-	-	-	<0.100	<3.50	<5.00	<5.00	-	-	-	-	-

UAE OFFICE:

Unite 801, Al Salemiyah tower, Rigga Al Buteen road, Dubai, United Arab Emirate, PO Box No: 384588

Website: essfuture.com

E-mail: info@essfuture.com

UAE TEL: +97508861747